

UPM Raflatac Technical Information

23-06-2025 EN SI EMEA

Face	RAFLATYRE-FSC
Sales Code	GWM
Product	Paper-based face with aluminium barrier to prevent plasticizer migration and improve adhesion to the tyre surface.
Use	Specially designed for labelling tyres and other rough rubber surfaces.

Typical technical values

Substance	81	g/m ²	ISO 536
Caliper	60	µm	ISO 534
Brightness	90	%	ISO 2470/1
Gloss	73	%	Hunter 75°

Printability	Suitable for flexo, letterpress and thermal transfer printing methods.
Sustainability	The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCH-COC-004879.
Disclaimer	The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.